

CONVEYOR BELTS

Series No.	Standard Widths [Met]	Nominal Thickness [μ]	Weight G/M ²	% Coating	Tensile Strength N/5cm	Dielectric Breakdown [Volts]
------------	-----------------------	-----------------------------	-------------------------	-----------	------------------------	------------------------------

Electrical Grade

7060	1/1.5	146	320	67	1100	4000
7110	1/1.5	275	600	66	2000	4500
9110-3	1/1.5/2/2.4	275	600	66	2000	4500

Premium Grade

7069	1/1.5	142	309	65	1100	3600
7109	1/1.5	245	534	61	2000	4000
9109-3	1/1.5/2/2.4	245	534	61	2000	4000
9119-3	1/1.5/2/2.4	260	550	63	2000	4300
9119-3FGBR	1/1.5/2/2.4	260	550	63	2000	N/A
7149	1/1.5/2.4	350	735	60	3000	3500
7159	1.5	380	820	64	3000	4000
7279*	2.6	685	1200	48	3000	4000

Standard Grade

9058	1/1.5/2/2.5	122	255	57	1100	2700
7068	1/1.5	138	296	63	1100	3600
7108	1/1.5	235	490	58	2000	3500
9108-3	1/1.5/2/2.4	235	490	58	2000	3500
7148	1/1.5/2.4	340	680	57	3000	3000
7278*	2.6	670	1085	43	3000	3500
7358	2	920	1380	38	5500	3000

Open Mesh

7195 Porous	1.5	670	520	21	3500	N/A
7195-1	1.5	670	676	39	3500	N/A
7255	2.5	770	445	26	1500	N/A
7305	2.7/3.2/3.7	980	460	32	1800	N/A
7305 AS	2.7/3.2	950	460	32	1600	N/A
7305 K	2.6	770	310	46	2500	N/A
7305 KG	3	1250	644	35	4500	N/A
9305	4.8	980	460	32	1800	N/A

Crease and Tear Resistant

9064	1/1.5	145	296	63	1100	3200
9104	1/1.5	240	490	59	1500	3500
9104-3	1/1.5	240	490	59	2000	3500

Anti-Static

9053	1/1.5/2/2.5	122	255	57	1100	N/A
7063	1/1.5	140	296	63	1100	N/A
9103-3**	1/1.5/2/2.4	235	490	58	2000	N/A
9113-3**	1/1.5/2/2.4	260	550	63	2000	N/A
7143**	1/1.5/2.4	340	680	57	3000	N/A
7153**	1/1.5/2.4	350	735	60	3000	N/A
7273*	2.6	680	1085	43	3500	N/A

Kevlar Fabrics

706K HT	1.27	150	200	62	1500	2000
715K	2	370	475	52	5000	2000
715 KAS	2	370	570	59	5000	N/A
717 K-1	1.6	430	720	63	2800	3000
717 KAS	1.5	420	630	57	2800	N/A

* 27 mil fabrics available in a variety of finishes, details on request.

** Also available with PTFE Top Coat

Nominal thickness, tensile strength and dielectric breakdown values are for a guideline only and are not intended as a specification minimum. For a full, current product specification sheet, please contact our customer services department.

Available widths are subject to change from time to time. Certain widths may be discontinued, while other widths not quoted above may become available. Details on request.

Weight g/m² +/-5% process variation

PTFE Content +/- 2% process variation

This document was created with Win2PDF available at <http://www.win2pdf.com>.
The unregistered version of Win2PDF is for evaluation or non-commercial use only.
This page will not be added after purchasing Win2PDF.